



FIRETEX[®] FX1003/FX2003

Solvent based intumescent coating designed for internal and external environments.



Formulated using **solvent borne acrylic resin technology** these materials offer a **highly versatile solution** to meet fire protection requirements from 15 to 120 minutes.


The testing of these products includes **elemental multi-temperature** evaluation meaning they can be used on **simple rolled steel members** and also beams including **complex arrangements of openings (cellular beams)**.

- FIRETEX[®] FX1003 – On-site
- Certified loadings for periods of 15 to 120 minutes. It is specifically formulated for on-site application, employing a high flash point solvent blend.
- FIRETEX[®] FX2003 – Off-site
- Certified loadings for periods of 15 to 120 minutes. It is specifically formulated for use in a paint shop environment, using a solvent blend developed to minimise the drying time and maximise shop throughput.



Volume reduction, save time & £££'s

- Lower loadings for effective fire protection.
 - Greater design flexibility.
 - Optimised specifications.
 - Single coat coverage.
- Increased application throughput.
 - Speed up project completion.
 - Fewer coats, reducing downtime.



Up to two hours protection

- Designed for cellulosic fire protection.
 - Competitive solutions from 15 to 120 minutes Passive Fire Protection.
 - Long lasting durability – up to 20 years in an external environment.
- Fully tested for your reassurance.
 - ISO BS476 Part 20/21.
 - ISO 12944-2 – up to C4.
 - Assessed to ASFP Yellow Book 5th Edition.





FIRETEX® FX1003/FX2003

Solvent based intumescent coating designed for internal and external environments.



Technical information

Recommended use	Solvent based intumescent coating providing passive fire protection from 15 to 120 minutes. FIRETEX® FX1003 – On-site application. FIRETEX® FX2003 – Off-site application.
Fire protection	15 to 120 minutes.
Certification	Certifire approved CF5077.
Durability	Life of building C1 environment*. Up to 20 years C2/C4 environment*.
Volume solids	75%.
Recommended primers	FIRETEX® C69, Macropoxy™ C400 Series. Consult a Sherwin-Williams' representative for alternative primers.
Approved topcoats	FIRETEX® M71V2 (C1/C2 environment), Acrolon™ C137V2/C237 (C3/C4 environment).
Application	Single component airless spray.
DFT (µm)	Film thickness calculated on section size and fire rating.
Time to touch dry	FIRETEX® FX1003 – 30mins @ 23°C
	FIRETEX® FX2003 – 20mins @ 23°C
Time to recoat	FIRETEX® FX1003 – 4hrs @ 23°C
	FIRETEX® FX2003 – 4hrs @ 23°C
Time to handle	This will depend on the total thickness of FIRETEX® FX1003/FX2003 to be applied.

The Sherwin-Williams Company

With over 150 years experience in the coatings industry we understand how critical it is that your investment gives you a quality, long term fire protection system, which performs in demanding environments.

Whether you specify FIRETEX® alone or in conjunction with Sherwin-Williams exceptional primers and topcoats, you can be assured that you are selecting a passive fire protection system that has been researched, developed and tested to the highest international standards.

Speak to your Sherwin-Williams representative to get an estimate on your next project using FIRETEX® intumescent materials.

To learn more, contact us

Europe, Middle East & Africa: +44 (0)1204 521771

North America: +1 800 524 5979

Asia: +8 621 5158 7798

sales.uk@sherwin.com

www.sherwin-williams.com/protectiveEMEA

* with appropriate maintenance.

TM = is a registered trademark in one or more countries.

©2016 The Sherwin-Williams Company
Protective & Marine Coatings

3/16 - EMEA0113/V03



www.sherwin-williams.com/protectiveEMEA

Protective & Marine Coatings
Europe, Middle East & Africa