

Hollow Section Columns & Beams						
Solids Content (%)			68			
Specific Gravity (Kgs/Ltr)			1.27			
Section Factor	Hp/A		DFT Micron	WFT Micron	Coverage Ltr/Sq.m	Coverage Kg/Sq.m
	From	To				
	0	45	540	803	0.803	1.019
	46	50	620	921	0.921	1.169
	51	55	710	1055	1.055	1.339
	56	60	790	1174	1.174	1.490
	61	65	870	1293	1.293	1.641
	66	70	960	1427	1.427	1.811
	71	75	1040	1545	1.545	1.962
	76	80	1120	1664	1.664	2.112
	81	85	1200	1783	1.783	2.263
	86	90	1290	1917	1.917	2.433
	91	95	1370	2036	2.036	2.584
	96	100	1450	2155	2.155	2.735
	101	105	1540	2288	2.288	2.905
	106	110	1620	2407	2.407	3.058
	110	115	1700	2526	2.526	3.206
	116	125	1750	2601	2.601	3.301
	126	130	1800	2675	2.675	3.395
	131	140	1850	2749	2.749	3.489
	141	150	1900	2823	2.823	3.583
	151	160	1950	2898	2.898	3.678
	161	165	2000	2972	2.972	3.772
	166	175	2050	3046	3.046	3.866
	176	185	2100	3121	3.121	3.961
	186	195	2150	3195	3.195	4.055
	196	200	2200	3269	3.269	4.149
	201	210	2250	3344	3.344	4.244
	211	220	2300	3418	3.418	4.338
	221	230	2350	3492	3.492	4.432
	231	240	2400	3566	3.566	4.526
	241	245	2450	3641	3.641	4.621
	246	255	2500	3715	3.715	4.715
	256	265	2550	3789	3.789	4.809
	266	275	2600	3864	3.864	4.904
	276	280	2650	3938	3.938	4.998
	281	290	2700	4012	4.012	5.092
	291	300	2750	4087	4.087	5.187
	301	310	2800	4161	4.161	5.281
	311	315	2850	4235	4.235	5.375
	316	325	2900	4309	4.309	5.469
	326	335	2950	4384	4.384	5.564
	336	345	3000	4458	4.458	5.658
	346	350	3050	4532	4.532	5.752
	351	360	3100	4607	4.607	5.847
	361	370	3150	4681	4.681	5.941
	371	380	3200	4755	4.755	6.035
	381	390	3250	4830	4.830	6.130
	391	395	3330	4948	4.948	6.224
	396	405	3350	4978	4.978	6.318
	406	415	3400	5052	5.052	6.412
	416	425	3450	5127	5.127	6.507
	426	430	3500	5201	5.201	6.601

Hollow Section Columns for 60 Mins FRP

Phoenix 167 - 60 minute FRP